Vision: to be your reliable supplier from China
Mission: to provide the best Made in China Product and Service
Philosophy: Rooting in China, linking with the world

BH110 TECHNICAL DATA SHEET

1.DESCRIPTION

FR BH110 is a synthetic high-performanced breathable housewrap. BH110 offers architects, specifiers and builders an advanced drainage solution that actually channels liquid away from the wall assembly at greater than 98% efficiency. BH110 is high strength, light weight, durable for up to 6 months UV exposure and has a 30 years limited warranty. BH110 is a 100% recyclable product. This is far better performance than that required by any code in the country. With a balance of breathability and water protection, DB110 Drainable is well-suited to most climates and exterior claddings.

2.TECHNICAL DATA SHEET **ASTM Standards and Test** No Characteristic Results **Industry Standard** Method ASTM E96 Procedure >70g/sm/day 35g/sm/day Moisture Vapor Transmission A(Desiccant Method) (>10 perms) (minimum 5 perms) Air Permeance at 75 Pascals **ASTM E2178** 0.002L/s/sqM <0.02L/s/sqM MD-60 lbf MD-40 lbf 3 ASTM D5034(Grab Test) **Dry Breaking Force** CD-45 lbf CD-35 lbf 10 min (minimum) Water Resistance "Boat Test" ASTM D779 Pass Hydrosatic Head Water AATCC 127 Pass (60 min rating) 55cm for 5 hours CCMC 07102 Pass (>24 hours) Pass (>2 hours) **Ponding** Class A Class A Flame Spread ASTM E84 Pass 0-25 Smoke Developed ASTM E84 Pass 0-450

Remark:DB110 is available in other sizes. Contact your products representative for details.

3.DISCLAIMER

Rev: March 8,2018

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.

feilereach@126.com www.feilereach.com